



(19)

(11) Publication number: **01315361**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**(21) Application number: **63145061**(51) Intl. Cl.: **B05B 5/04 B05D 1/04 B05D 1/40**(22) Application date: **13.06.88**

(30) Priority:

(43) Date of application  
publication: **20.12.89**(84) Designated contracting  
states:(71) Applicant: **TOYOTA MOTOR CORP**(72) Inventor: **OHASHI YUTAKA  
FUKUDA TOKUHITO**


(74) Representative:

**(54) METHOD AND  
APPARATUS FOR ROTARY  
ATOMIZATION  
ELECTROSTATIC  
COATING**

(57) Abstract:

**PURPOSE:** To secure required lightness of metallic coating by setting the relation of both the number of revolutions of a belllike cap and the radius thereof in the specified relation and controlling shaping air so that air velocity of the vertical direction on the surface of a material to be coated is regulated to specified value or more.

**CONSTITUTION:** The relation of both the number of revolutions  $C$  (revolution/ second) of a belllike cap 3 and the radius  $R$  (m) thereof is set in  $R \times C^2 \leq 5000$  preferably  $R \times C^2 \leq 2000$ . Furthermore shaping air of a rotary atomization electrostatic coating apparatus is controlled so that air velocity of the vertical direction



on the surface of a material to be coated is regulated to  $\geq 10\text{m/second}$  preferably  $\geq 15\text{m/second}$ . As a result, breaking and deformation of pigment are inhibited and thereby required lightness can be secured even when metallic coating is coated.

COPYRIGHT: (C)1989,JPO&Japio

